

# EUROPEAN PATENT OFFICE

## Patent Abstracts of Japan

PUBLICATION NUMBER : 62041257  
PUBLICATION DATE : 23-02-87

APPLICATION DATE : 15-08-85  
APPLICATION NUMBER : 60180126

APPLICANT : MATSUSHITA ELECTRIC WORKS LTD;

INVENTOR : MINAMIHAMA MASANORI;

INT.CL. : C08L 67/06

TITLE : RESIN COMPOSITION

ABSTRACT : PURPOSE: To provide a resin compsn. which has excellent dimensional stability, smoothness, colorability and gloss, scarcely causes unevenness and is not cured within cylinders when injection-molded, by blending PE with a resin compsn. consisting of an unsaturated polyester, a copolymerizable monomer and PS.

CONSTITUTION: 100pts.wt. unsaturated polyester (A) having an average MW of 1,500~2,000 and an acid value of 18~22, obtd. by the polycondensation reaction of fumaric acid, propylene glycol and diethylene glycol, 80~30pts.wt. monomer (B) copolymerizable therewith (e.g., styrene) and 30~80pts.wt. polystyrene (C) having an MW of 150,000~200,000 as a shrinkage controlling agent are blended to obtain a resin compsn. 0.5~3.0wt% PE powder, a polymn. initiator (e.g., dicumyl peroxide), a filler (e.g., aluminum hydroxide), a parting agent (e.g., stearic acid or zinc stearate), etc., are blended with 18~28wt% said compsn. to obtain a resin compsn. which can be used as an injection molding material (premix).

COPYRIGHT: (C)1987,JPO&Japio

*radical generator.*